


EGE SERAMİK PACKING AND TECHNICAL SPECIFICATIONS

SIZE	TYPE	PEI VALUE	WET (COF'S)	DRY (COF'S)	WATER ABSORPTION	SCRATCH HARDNESS (MOH'S)	SHADE VARIATION (CTDA)	BREAKING STRENGTH (LBF)	CHEMICAL RESISTANCE
13X13	glazed porcelain	4	0.64-0.69	0.65-0.70	0.22%	8	v3	400	resistant
18X18	glazed porcelain	4	0.64-0.69	0.65-0.70	0.32%	8	v3	440	resistant
24x24	glazed porcelain	4	0.64-0.69	0.65-0.70	0.30%	8	v3	433	resistant

SIZE	TYPE	LBS/PCE	PCS/BOX	LBS/BOX	BOX/PLT	SQ.FT/BOX	SQ.FT/PLT	NET LBS/PLT	GROSS LBS. PLT	PLT/CTN 20FT.	LBS/CTN 20FT.	SQ.FT/CTN 20FT.	PALLET HEIGHT (31x47x...)
13x13	glazed porcelain	4.17	9	37.52	62.00	10.76	667.36	2,326.41	2,370.50	20	47,409.98	13,347.25	31.89
18x18	glazed porcelain	8.55	7	59.88	52.00	15.26	793.41	3,113.63	3,157.73	15	47,365.88	11,901.12	41.73
24x24	glazed porcelain	16.89	4	67.55	32	15.50	496	2,161.59	2,205.68	21	46,319.31	10,416.02	29.13