


EGESERAMİK PACKING AND TECHNICAL SPECIFICATIONS

SIZE	TYPE	PEI VALUE	WET (COF'S)	DRY (COF'S)	WATER ABSORPTION	SCRATCH HARDNESS (MOH'S)	SHADE VARIATION (CTDA)	BREAKING STRENGTH (LBF)	CHEMICAL RESISTANCE
4x24	glazed porcelain	4	0.60-0.65	0.73-0.78	0.27%	8	v2	466	resistant
5x24	glazed porcelain	4	0.60-0.65	0.73-0.78	0.27%	8	v2	466	resistant
6x24	glazed porcelain	4	0.60-0.65	0.73-0.78	0.27%	8	v2	466	resistant

SIZE	TYPE	LBS/PCE	PCS/BOX	LBS/BOX	BOX/PLT	SQ.FT/BOX	SQ.FT/PLT	NET LBS/PLT	GROSS LBS. PLT	PLT/CTN 20FT.	LBS/CTN 20FT.	SQ.FT/CTN 20FT.	PALLET HEIGHT (31x47x...)
4x24	glazed porcelain	2.80	10	28.02	72	6.46	465	2,017.49	2,061.59	22	45,354.92	10,230.02	29.92
5x24	glazed porcelain	3.47	10	34.72	60	8.07	484.38	2,083.37	2,127.46	22	46,804.15	10,656.27	31.10
6x24	glazed porcelain	4.25	10	42.48	48	9.69	465	2,039.19	2,083.28	22	45,832.17	10,230.02	29.92